
## Resistors



### **WBC Capacitor Series**

- Silicon Dioxide/Silicon Nitride dielectric
- Capacitance range from 10pF to 1000pF
- Silicon substrate with gold or aluminum backing







All parts are Pb-free and comply with EU Directive 2011/65/EU amended by (EU) 2015/863 (RoHS3)

IRC's wire-bondable chip capacitors are based on the successful TaNCAP® line of RC networks on silicon. The new chip capacitors have the advantage of excellent performance in extremely small sizes ranging from 20 to 60 mils square.

Capacitors are 100% electrically tested with mil screening to MIL-STD-883 also available. For demanding hybrid circuit and/or chip and wire applications, specify IRC's WBC capacitor series.

### Physical Data





# Manufacturing Capabilities Data

Style	Size	Capacitance Range	Voltage
C0202	0.020"± 0.001 sq. (0.508mm ±0.025)	10pF to 51pF	40
C0303	0.030"± 0.001 sq. (0.762mm ±0.025)	33pF to 100pF	55
C0404	0.040″± 0.001 sq. (1.016mm ±0.025)	56pF to 220pF	50
C0505	0.055"± 0.001 sq. (1.397mm ±0.025)	160pF to 360pF	20
C0606	0.060"± 0.001 sq. (1.524mm ±0.025)	160pF to 1000pF	20

### **WBC Capacitor Series**



## **Electrical Data**

Capacitance Range	10pF to 1000pF	
Dissipation Factor 1Khz, +25°C, 1V <sub>RMS</sub>	0.5% min	
Absolute Tolerance	to ±5%	
Operating Temperature	-55°C to +125°C	
Noise	<-30dB	
Substrate Material	Semiconductor Silicon (10KÅ SiO <sub>2</sub> minimum)	
Substrate Thickness	0.010″ ±0.001 (0.254mm ±0.025)	
Bond Pad Metallization	Aluminum: 10KÅ minimum	
Backside	Aluminum: 10KÅ minimum Gold: 3KÅ minimum	
Dielectric	Silicon Dioxide and/or Silicon Nitride	
Passivation	Silicon Dioxide or Silicon Nitride	

## **Environmental Data**

Test	Method	Max ∆C	
Thermal Shock	MIL-STD-202 Method 107 Test condition F	±0.25% + 0.25pF max	
Moisture Resistance	MIL-STD-202 Method 106	±1.0% + 0.25pF max	
Short Time Overload	+25°C, 5 seconds 1.5 X rated voltage	±0.25% + 0.25pF mx	
Life at Elevated Temperature	MIL-STD-202 Method 108 125°C, 1000 hours	±0.25% + 0.25pF max	
High Temperature Exposure	100 hours @ 150°C ambient	±0.25% + 0.25pF max	

# **Ordering Data**

Prefix····· WBC - C0606	A G	- 102 - K
Style		
Bonding pads···· A = Aluminum		
Backside	<b>.</b>	
<b>Capacitance</b> 3-Digit Capacitance Code Ex: 102 = 1000pF; 221 = 220pF; 470 = 47pF	• • • • • • •	
Absolute Tolerance Code · · · · · · · · · · · · · · · · · · ·	• • • • • •	•

Packaging
Standard packaging is 2" x 2" chip tray. For additional information or to discuss your specific requirements, please contact our Applications Team using the contact details below.