

Model 64LF BOM-style material declaration. BI Technologies Corporation

9/2/2010

No content here is banned per E.U. R.o.H.S.. Average mass of 64LF trimmer is 0.4 grams each. Prepared by Eric Arnold (714) 447-2565
Weights above 1 milligram rounded to the nearest mg. Values less than 1 milligram given in scientific notation.

Sub-component	Material	% of total mass	Substance name	CAS #	Substance Weight (grams)	Special classification		
Housing	PBT blend	40.3%	PBT	26062-94-2	0.129			
			Fiberglass	65997-17-3	0.034			
			SbO	1309-64-4	0.009	Fire retardant		
Shaft	Brass	9.7%	Cu	7440-50-8	0.026			
			Zn	7440-66-6	0.015			
			Pb in brass	7439-92-1	0.001	Pb in copper alloy (RoHS exempt)		
	Cu plating	0.24%	Cu	7440-50-8	1.02E-03			
Ni plating	0.22%	Ni	7440-02-0	9.20E-04	exposed nickel			
Rotor	PTFE	8.9%	PTFE	009002-84-0	0.038			
Contact	Pd alloy wire	0.26%	Pd	7440-05-3	2.97E-04			
			Ag	7440-22-4	4.40E-04			
			Cu	7440-50-8	2.75E-04			
			Zn	7440-66-6	1.10E-05			
			Ni	7440-02-0	7.70E-05			
			Nickel alloy bar	0.23%	Cu	7440-50-8	5.00E-07	
					Ni	7440-02-0	8.46E-04	
	C	7440-44-0			6.00E-07			
	Mn	7439-96-5			2.50E-06			
	Fe	7439-89-6			1.50E-04			
	S	7704-34-9			5.00E-08			
	Terminals	Cu wire	10.2%	Cu	7440-50-8	0.043		
		Sn plating	0.004%	Sn	7440-31-5	1.73E-05		
Potting	Epoxy	12.1%	SiO2, amorphous	7631-86-9	0.003			
			modified aliphatic polyamine	trade secret	0.010			
			hydantoin epoxy resin	15336-82-0	0.003			
			epichlorohydrin / polyglycol epoxy resin	26142-30-3	0.003			
			epichlorohydrin/bisphenol A epoxy resin	unknown	0.031	BPA		
			cycloaliphatic epoxy resin	2386-87-0	0.003			
Substrate	Alumina	17.7%	Al2O3	1344-28-1	0.073			
			SiO2, amorphous	7631-86-9	7.56E-04			
			TiO2	13463-67-7	3.78E-04			
			FeO2	1345-25-1	3.78E-04			
			MnO2	1313-13-9	7.56E-04			
			MgO	1309-48-4	3.78E-04			
			CaO	1305-78-8	3.78E-04			
			Conductor	AgPd thick film	0.10%	Al2O3	1344-28-1	2.85E-06
SiO2, amorphous	7631-86-9	1.25E-05						
TiO2	13463-67-7	2.85E-06						
PbO	1317-36-8	1.70E-05				Pb in electronic ceramic (RoHS exempt)		
ZnO	1314-13-2	3.09E-06						
B2O3	1303-86-2	1.05E-06						
ZrO2	1314-23-4	2.52E-07						
BaO	1304-28-5	3.23E-06						
Ag	7440-22-4	3.39E-04						
Pd	7440-05-3	3.78E-05						
Resistor	Ruthenate thick film	0.07%				Al2O3	1344-28-1	4.25E-06
			SiO2, amorphous	7631-86-9	3.57E-05			
			TiO2	13463-67-7	4.25E-06			
			MnO2	1313-13-9	1.92E-06			
			PbO	1317-36-8	9.35E-05	Pb in electronic ceramic (RoHS exempt)		
			ZnO	1314-13-2	1.02E-05			
			B2O3	1303-86-2	1.19E-05			
			ZrO2	1314-23-4	2.86E-06			
			BaO	1304-28-5	4.83E-06			
			Ag	7440-22-4	1.15E-05			
			Pd	7440-05-3	1.47E-05			
			Steatite	14807-96-6	6.40E-07			
			Bi2Ru2O6	unknown	1.44E-05			
			Pb2Ru2O6+x	unknown	1.02E-04	Pb in electronic ceramic (RoHS exempt)		
			RuO2	12036-10-1	6.72E-06			